

TEST REPORT

Client Name : SHANDONG PENGCHENG INTERNATIONAL TRADE CO.,LTD.

Client Address : EHUANG ROAD, LANSHAN DISTRICT, LINYI, SHANDONG, CHINA
276000

Sample Name : PP Plastic Plywood

Sample No. : FAIRN16120030

Test type : Entrusted Test

Test Item(s) : Bend Test, Shear test

Date of Receipt : 2016/12/19

Test Period : 2016/12/19~2017/01/17

-To be continued-

Edited by Aimee Xu Checked by Lisa Xin Approved by Tweety.cn

青 岛 费 尔 检 测 科 技 有 限 公 司
QINGDAO FAIRTEST SCI & TECH CO., LTD.

检测专用章

声明: 委托检测的报告结果仅对来样负责。检测报告无本公司检测专用章无效。未经本公司书面批准, 不得部分复制检测报告。对检测报告书若有异议, 应于收到报告之日起十五日内向本公司提出。Declare: The result(s) of entrusted test report is only responsible for the received sample(s).

Test report without the test seal of the company is invalid. Test report should not be partly copied without the approval of the company. Any objection to this report should be put forward within 15 days after receiving this report.

TEST REPORT

Sample(s) and information were supplied by the client. Client is responsible for the authenticity of information and the representation of sample(s) :

Sample Name : PP Plastic Plywood


Product Specification : 19mm (3/4")

Material and Mark : Poplar wood + Polypropylene coating

Manufacturer : Shandong Fangyuan Building Materials Co.,Ltd.

Supplier : Shandong Fangyuan Building Materials Co.,Ltd.

Original Sample Photo(s) :



Conclusion : /

Test Result(s) : See next

1. Bend test

Test Method: GB/T 17657-2013 Clause 4.7

Test item	Static Bending Strength, Mpa	Elasticity Modulus, Mpa
Result	47.4	4970

-To be continued-

TEST REPORT

2. Shear test

Test Method: GB/T 17657-2013 Clause 4.18

Test item	Shear Strength, Mpa
Result	1.42

This test report is the English version of test report No.FAIRN16110030, If any difference, the Chinese version is the final decision.

-End of report-

